

# **Technical Information Sheet**



## UltraPly™ TPO QuickSeam™ Pipe Flashing

UltraPly TPO Molded QuickSeam Pipe Flashing W56TPO3033	Item Description	Item Number
	UltraPly TPO Molded QuickSeam Pipe Flashing	W56TP03033

#### Description

UltraPly TPO QuickSeam Pipe Flashings are specifically designed to be used on UltraPly TPO roofing applications for flashing of round penetrations. UltraPly TPO QuickSeam Pipe Flashings will fit various penetrations and must be cut to correct pipe diameter before installation.

### Method of Application

- 1. Clean and prime the UltraPly TPO membrane using Elevate Single Ply QuickPrime Primer or Single Ply LVOC Primer using a QuickScrubber<sup>™</sup> or QuickScrubber Plus pad and handle to remove all dusting agents, dirt and other contaminants that will affect the finished bond. **NOTE:** Heavy accumulation of contaminates may necessitate cleaning with Splice Wash or soap and water. Allow to dry completely before applying primer.
- 2. Allow primer to dry according to the touch-push test.
- 3. Cut along the top edge of the ring on the UltraPly TPO QuickSeam Pipe Flashing corresponding to the size of the pipe. **NOTE:** Make cut above rib.
- 4. Remove the release liner from the tape portion.
- 5. Install the pipe flashing and roll the flange with a silicone hand roller.
- 6. To ensure formability, slightly heat the surface of the pipe flashing flange at all steps and transitions using a hot air welder and re-roll.
- 7. Install the clamping ring and Elevate All-Purpose Sealant per Elevate Specifications and Details.
- 8. Install TPO QuickSeam T-Joint Patches to specification over any seams crossing beneath the boot flange.

#### Storage

- Store in original unopened can, at temperatures between 60 °F (16 °C) and 80 °F (27 °C) until ready for use.
- Do not store on roof in direct sunlight or at temperatures above 100 °F (38 °C).
- When exposed to lower temperatures, restore to room temperature prior to use.
- If exposed to lower temperatures, restore to room temperature prior to use.





## Shelf Life

Shelf life will be shortened if exposed to elevated temperatures. Shelf life of 24 months can be expected when stored in original container at temperatures between 60 °F (16 °C) and 80 °F (27 °C).

## Packaging

10 UltraPly QuickSeam Pipe Flashings / 10 stainless steel clamps - per carton

## **Precautions**

- Review TPO QuickSeam Safety Data Sheet prior to use.
- Not intended for use on uneven substrates (i.e., through steps or angle changes).
- Refer to Safety Data Sheets (SDS) for additional safety information.

## LEED<sup>®</sup> Information

Post-Consumer Recycled Content:0%Post Industrial Recycled Content:0%Manufacturing Location:Bensenville, ILNOTE: LEED® is a registered trademark of the U.S. Green Building Council

Typical Properties			
Properties	Value		
Molded Pipe Flashing			
Base	Thermoplastic Polyolefin (TPO)		
Color	White		
Sizes	Universal – Fits 1" O.D. to 6" O.D. (25.4 mm to 152.4 mm)		
Clamp	Stainless Steel – worm gear type (clamps are included)		
Pipe Flange	13" (33 cm) outside diameter		
Thickness	0.055"-0.075" (1.4 mm – 1.9 mm)		
QuickSeam Tape	;		
Base	Rubber Polymer		
Color	White		
Solvents	None		
Percent Solids	100%		
Cured State	Cured		
Thickness	0.030" (0.762 mm) + 0.005" (0.13 mm)		

Fits the Pipe Sizes	
1" (25.4 mm)	
1.5" (38.1 mm)	
2" (50.8 mm)	
3" (76.2 mm)	
4" (101.6 mm)	
5" (127 mm)	
6" (152.4 mm)	

Please contact Holcim Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight Elevate products and specifications and is subject to change without notice. Holcim takes responsibility for furnishing quality materials that meet published Elevate product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Holcim nor its representatives practice architecture. Holcim offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Holcim accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Holcim representative is authorized to vary this disclaimer.

